

Honeycomb ivory foam

Technical Data Sheet (EP25-OL)

Quality: PE/EVA		Color: colorful
Classification :ASTM		Passed at 6.0mm thickness
PE/EVA series	Standard	
Material base	ISO 1629	Blend Ethylene vinyl acetate and Polyethylene (EVA/PE)
General description	Without Standard	Closed cell , Middle Hardness , Elastic, Sulfur free, Low odor
Density	Without Standard	$150 \pm 25 \text{ kg/m}^3$
Application temperature	Without Standard	-40 to +90 °C
Ozone resistance	ISO1431	200pphm /48hr/%20St/40°C/Static No crack
Outdoor exposure	ISO 877	Very good weather resistance
Shore hardness	Shore C	40 to 60
Water absorption	ASTM D1056	≤ 10
Form of delivery	Block size with production skin 2500 x 1500 x 20 mm, The material can be further processed by splitting, cutting, sawing, punching, gluing, Layers, and coating with adhesives. General dimensional tolerances for sheet and sheet products comply with DIN 7715 P3, dimensional tolerances for the block material may differ.	
Examples for chemical resistances	Acids and bases in common concentrations, water, water steam up to 100 °C, sea water, potassium and sodium compounds, alum aqueous, detergent, photographic chemicals, ammonia cold, acetylene, alcohols, glycerine, glycol-based anti-freeze, carbonic acid, ozone, silicone oil, bleaching powder aqueous.(limited deployable) Chlorine gas, ammonia hot, conc. hydrochloric acid.(not recommended) Oils, greases, mineral spirits, solvents such as toluene, dichloromethane, trichloroethylene, perchloroethylene (PER), cellulose thinners, conc. nitric and sulfuric acid.	